

EcoSoya Technical Data Sheet

Date Prepared: 23APR20

Date Revised: N/A

Version: 1.0

TDS – EcoSoya Melt

Information

Product Description

EcoSoya Melt is formulated for use in the manufacture of fragranced melts.

Physical Properties

Test	Method	Typical Value
Congealing Point, °C	ASTM D938	51
Viscosity @ 100°C, cSt	ASTM D445	9.7
Penetration @ 25°C, dmm	BS 1426	29
Colour	Visual	Off White

Statement

- Formulated from materials whose refining history is fully traceable.
- Does not contain or come into contact with any animal or GMO products at any stage of its manufacture
- Does not contain residual solvents as per guidelines CPMP/ICH283/95.
- Has not been tested on animals by ourselves or on our behalf.